

In the Claims:

Please amend claims 1 and 17 to 20 as follows:

1. (currently amended) An optical element for an optical data transfer device said optical element comprising an optical glass with an index of refraction (n_d) greater than or equal to 1.70, an Abbé number (v_d) greater than or equal to 35 and a density (ρ) that is less than or equal to 4.5 g/cm^3 ,

wherein said optical glass has a composition, in weight percent on an oxide basis, comprising:

<u>La_2O_3</u>	<u>30 to 55</u>
<u>B_2O_3</u>	<u>20 to 40</u>
<u>SiO_2</u>	<u>0 to 8</u>
<u>PbO</u>	<u>0 to 5</u>
<u>MgO</u>	<u>0 to 8</u>
<u>CaO</u>	<u>0 to 8</u>
<u>SrO</u>	<u>0 to 8</u>
<u>BaO</u>	<u>0 to 8</u>
<u>ZnO</u>	<u>0 to 10</u>
<u>TiO_2</u>	<u>0 to 5</u>
<u>ZrO_2</u>	<u>0 to 10</u>
<u>GeO_2</u>	<u>0 to 15</u>
<u>Y_2O_3</u>	<u>0 to 11</u>

<u>Yb₂O₃</u>	<u>0 to 5</u>
<u>Gd₂O₃</u>	<u>0 to 5</u>
<u>Nb₂O₅</u>	<u>0 to 10</u>
<u>with MgO+CaO+SrO+BaO</u>	<u>0 to 10.</u>

2. (previously presented) The optical element as defined in claim 1, wherein said Abbé number (v_d) is greater than or equal to 40.

3. (previously presented) The optical element as defined in claim 1, wherein said density (ρ) that is less than or equal to 4.3 g/cm³.

4. (canceled)

5. (withdrawn) A read-and-write device for optical data transfer, said read-and-write device comprising an optical glass with an index of refraction (n_d) greater than or equal to 1.70, an Abbé number (v_d) that is greater than or equal to 35 and a density (ρ) that is less than or equal to 4.5 g/cm³.

6. (withdrawn) The read-and-write device with a movable read-write head and at least one optical element, said at least one optical element comprising an optical glass with an index of refraction (n_d) greater than or equal to 1.70, an Abbé number (v_d) greater than or equal to 35 and a density (ρ) is less than or equal to

4.5 g/cm³.

Claims 7 to 15. (canceled)

16. (previously presented) The optical element as defined in claim 1, wherein said optical glass is a lanthanate borate glass, said lanthanate borate glass necessarily comprises La₂O₃, B₂O₃ and ZrO₂ and said lanthanate borate glass includes either Y₂O₃ or Nb₂O₅, and wherein a sample of said lanthanate borate glass with a 25 mm thickness has a spectral transmission purity degree of at least percent 70.8 percent at a wavelength of 400 nm and a partial dispersion of no more than 0.567 in the blue spectral region.

17. (currently amended) An optical element for an optical data transfer device said optical element comprising an optical glass with an index of refraction (n_d) greater than or equal to 1.70, an Abbé number (v_d) greater than or equal to 35 and a density (ρ) that is less than or equal to 4.5 g/cm³ ~~The optical element as defined in claim 1, wherein said optical glass is a lanthanate borate glass with a composition, in percent by weight based on oxide content, which consists of:~~

La ₂ O ₃	30 to 45
B ₂ O ₃	30 to 40
Al ₂ O ₃	0 to 5
PbO	0.1 to 5

Li ₂ O	0 to 10
Na ₂ O	0 to 10
K ₂ O	0 to 10
Rb ₂ O	0 to 10
Cs ₂ O	0 to 10
MgO	0 to 8
CaO	0 to 8
SrO	0 to 8
BaO	0 to 8
ZnO	1 to 10
TiO ₂	0 to 5
ZrO ₂	1 to 10
Y ₂ O ₃	1 to 8
Yb ₂ O ₃	0.1 to 2
Gd ₂ O ₃	0.1 to 5
Nb ₂ O ₅	0.1 to 10
with MgO+CaO+SrO+BaO	0 to 10
with Li ₂ O+Na ₂ O+K ₂ O+Rb ₂ O+Cs ₂ O	0 to 10;

and from 0 to 1.5 percent by weight of at least one refining agent, wherein said at least one refining agent is selected from the group consisting of SO₄⁻², Cl⁻, Sb₂O₃, As₂O₃, SnO₂ and CeO₂.

18. (currently amended) An optical element for an optical data transfer device
said optical element comprising an optical glass with an index of refraction (n_d)
greater than or equal to 1.70, an Abbé number (v_d) greater than or equal to 35
and a density (ρ) that is less than or equal to 4.5 g/cm³ ~~The optical element as~~
~~defined in claim 1, wherein said optical glass is a lanthanate borate glass with a~~
composition, in percent by weight based on oxide content, which consists of:

La ₂ O ₃	35 to 50
B ₂ O ₃	30 to 40
Al ₂ O ₃	0 to 5
SiO ₂	0 to 8
GeO ₂	0.5 to 15
Li ₂ O	0 to 10
Na ₂ O	0 to 10
K ₂ O	0 to 10
Rb ₂ O	0 to 10
Cs ₂ O	0 to 10
SrO	0 to 2
BaO	0.1 to 7
ZnO	0 to 5
ZrO ₂	0.1 to 8
Y ₂ O ₃	0.1 to 6
Gd ₂ O ₃	0 to 5

Nb₂O₅ 1 to 10

With Li₂O+Na₂O+K₂O+Rb₂O+Cs₂O 0 to 10;

and from 0 to 1.5 percent by weight of at least one refining agent, wherein said at least one refining agent is selected from the group consisting of SO₄⁻², Cl⁻, Sb₂O₃, As₂O₃, SnO₂ and CeO₂.

19. (currently amended) An optical element for an optical data transfer device said optical element comprising an optical glass with an index of refraction (n_d) greater than or equal to 1.70, an Abbé number (v_d) greater than or equal to 35 and a density (ρ) that is less than or equal to 4.5 g/cm³ ~~The optical element as defined in claim 1,~~ wherein said optical glass is a lanthanate borate glass with a composition, in percent by weight based on oxide content, which consists of:

La₂O₃ 40 to 55

B₂O₃ 22 to 32

Al₂O₃ 0 to 5

SiO₂ 1 to 8

Li₂O 0 to 10

Na₂O 0 to 10

K₂O 0 to 10

Rb₂O 0 to 10

Cs₂O 0 to 10

SrO	0 to 8
BaO	0 to 2
ZnO	0.5 to 6
TiO ₂	0 to <u>[[3]] 1.0</u>
ZrO ₂	2 to 10
Y ₂ O ₃	3 to 11
With Li ₂ O+Na ₂ O+K ₂ O+Rb ₂ O+Cs ₂ O	0 to 8;

and from 0 to 1.5 percent by weight of at least one refining agent, wherein said at least one refining agent is selected from the group consisting of SO₄⁻², Cl⁻, Sb₂O₃, As₂O₃, SnO₂ and CeO₂.

20. (currently amended). An optical element for an optical data transfer device
said optical element comprising an optical glass with an index of refraction (n_d)
greater than or equal to 1.70, an Abbé number (v_d) greater than or equal to 35
and a density (ρ) that is less than or equal to 4.5 g/cm³ The optical element as
defined in claim 1, wherein said optical glass is a lanthanate borate glass with a
composition, in percent by weight based on oxide content, which comprises
consists of:

La ₂ O ₃	10 to 16
B ₂ O ₃	1 to 8
Al ₂ O ₃	0 to 3

SiO ₂	20 to 30
Li ₂ O	0 to 10
Na ₂ O	0 to 10
K ₂ O	0 to 10
Rb ₂ O	0 to 10
Cs ₂ O	0 to 10
SrO	0 to 8
BaO	0 to 8
ZnO	1 to 8
ZrO ₂	0.5 to 6
TiO ₂	3 to 11
Nb ₂ O ₅	10 to 18
With Li ₂ O+Na ₂ O+K ₂ O+Rb ₂ O+Cs ₂ O	0 to 8;

and from 0 to 1.5 percent by weight of at least one refining agent, wherein said at least one refining agent is selected from the group consisting of SO₄⁻², Cl⁻, Sb₂O₃, As₂O₃, SnO₂ and CeO₂.

21. (withdrawn) The read-and-write device as defined in claim 5 or 6, wherein said density (ρ) that is less than or equal to 4.3 g/cm³.

22. (withdrawn) The read-and-write device as defined in claim 5 or 6, wherein a sample of said optical glass with a 25 mm thickness has a spectral transmission

purity degree of at least percent 70.8 percent at a wavelength of 400 nm and a partial dispersion of no more than 0.567 in the blue spectral region.

23. (withdrawn) The read-and-write device as defined in claim 5 or 6, wherein said optical glass is a lanthanate borate glass, said lanthanate borate glass necessarily comprises La_2O_3 , B_2O_3 and ZrO_2 and said lanthanate borate glass includes either Y_2O_3 or Nb_2O_5 .

24. (withdrawn) The read-and-write device as defined in claim 5, wherein said optical glass is a lanthanate borate glass with a composition, in percent by weight based on oxide content, which consists of:

La_2O_3	30 to 45
B_2O_3	30 to 40
Al_2O_3	0 to 5
PbO	0.1 to 5
Li_2O	0 to 10
Na_2O	0 to 10
K_2O	0 to 10
Rb_2O	0 to 10
Cs_2O	0 to 10
MgO	0 to 8
CaO	0 to 8
SrO	0 to 8

BaO	0 to 8
ZnO	1 to 10
TiO ₂	0 to 5
ZrO ₂	1 to 10
Y ₂ O ₃	1 to 8
Yb ₂ O ₃	0.1 to 2
Gd ₂ O ₃	0.1 to 5
Nb ₂ O ₅	0.1 to 10
with MgO+CaO+SrO+BaO	0 to 10
with Li ₂ O+Na ₂ O+K ₂ O+Rb ₂ O+Cs ₂ O	0 to 10;

and from 0 to 1.5 percent by weight of at least one refining agent, wherein said at least one refining agent is selected from the group consisting of SO₄⁻², Cl⁻, Sb₂O₃, As₂O₃, SnO₂ and CeO₂.

25. (withdrawn) The read-and-write device as defined in claim 5, wherein said optical glass is a lanthanate borate glass with a composition, in percent by weight based on oxide content, which consists of:

La ₂ O ₃	35 to 50
B ₂ O ₃	30 to 40
Al ₂ O ₃	0 to 5
SiO ₂	0 to 8
GeO ₂	0.5 to 15

Li_2O	0 to 10
Na_2O	0 to 10
K_2O	0 to 10
Rb_2O	0 to 10
Cs_2O	0 to 10
SrO	0 to 2
BaO	0.1 to 7
ZnO	0 to 5
ZrO_2	0.1 to 8
Y_2O_3	0.1 to 6
Gd_2O_3	0 to 5
Nb_2O_5	1 to 10
With $\text{Li}_2\text{O}+\text{Na}_2\text{O}+\text{K}_2\text{O}+\text{Rb}_2\text{O}+\text{Cs}_2\text{O}$	0 to 10;

and from 0 to 1.5 percent by weight of at least one refining agent, wherein said at least one refining agent is selected from the group consisting of SO_4^{-2} , Cl^- , Sb_2O_3 , As_2O_3 , SnO_2 and CeO_2 .

26. (withdrawn) The read-and-write device as defined in claim 5, wherein said optical glass is a lanthanate borate glass with a composition, in percent by weight based on oxide content, which consists of:

La_2O_3	40 to 55
B_2O_3	22 to 32

Al_2O_3	0 to 5
SiO_2	1 to 8
Li_2O	0 to 10
Na_2O	0 to 10
K_2O	0 to 10
Rb_2O	0 to 10
Cs_2O	0 to 10
SrO	0 to 8
BaO	0 to 2
ZnO	0.5 to 6
TiO_2	0 to 3
ZrO_2	2 to 10
Y_2O_3	3 to 11
With $\text{Li}_2\text{O}+\text{Na}_2\text{O}+\text{K}_2\text{O}+\text{Rb}_2\text{O}+\text{Cs}_2\text{O}$	0 to 8;

and from 0 to 1.5 percent by weight of at least one refining agent, wherein said at least one refining agent is selected from the group consisting of SO_4^{-2} , Cl^- , Sb_2O_3 , As_2O_3 , SnO_2 and CeO_2 .

27. (withdrawn) The read-and-write device as defined in claim 5, wherein said optical glass is a lanthanate borate glass with a composition, in percent by weight based on oxide content, which consists of:

La_2O_3	10 to 16
-------------------------	----------

B_2O_3	1 to 8
Al_2O_3	0 to 3
SiO_2	20 to 30
Li_2O	0 to 10
Na_2O	0 to 10
K_2O	0 to 10
Rb_2O	0 to 10
Cs_2O	0 to 10
SrO	0 to 8
BaO	0 to 8
ZnO	1 to 8
ZrO_2	0.5 to 6
TiO_2	3 to 11
Nb_2O_5	10 to 18
With $Li_2O+Na_2O+K_2O+Rb_2O+Cs_2O$	0 to 8;

and from 0 to 1.5 percent by weight of at least one refining agent, wherein said at least one refining agent is selected from the group consisting of SO_4^{-2} , Cl^- , Sb_2O_3 , As_2O_3 , SnO_2 and CeO_2 .